

EUROTHANE POLYURETHANE PAINTS ACRYLIC ALIPHATIC POLYURETHANE FINISHING PAINT

Composition

Acrylic modified, non-yellowing, aliphatic isocynate based polyurethane two component coating available in customized shades and gloss levels.

> Recommended Applications

This product is recommended as top coat for the long term protection of steel, concrete and other surfaces exposed to highly corrosive, marine and chemical environments. It has got very good weathering resistance along with chemical, water and solvent resistance. It is recommended for chemical processing industries, food processing industries, pharmaceutical industries, off-shore and on-shore structures and marine industries, cement plants, storage tanks exteriors, oil & gas and petrochemical refineries and on transports vehicles.

> Technical Data

COLOUR : Assorted shades as per requirements
FINISH : Full glossy to matt as per requirements
SOLIDS BY VOLUME : 40 ± 2% depends upon shade and gloss

levels

THEORETICAL SPREADING RATE : 12.6 to 14.0 sq. Mtr/ ltr@ dft of 30

microns

IIICIOII

FLASH POINT : Above 22^oc for base & hardener

DRYING CHARACTERISTICS : Surface dry : 30-45 minutes (at 30°c & 65% relative humidity) Dry to overcoat : 4-6 hours Hard dry : 18-24 hours

Full cure : 7 days

MIXING RATIO (base: hardener) : 3:1 by volume

APPLICATION : By brush, spray and airless spray

THINNER : Pu thinner 099

SELF LIFE : 6 months for both the components in

Originally sealed containers.

POT LIFE : 4-6 hours at 30° c

Typical Application Systems And Equipments

It is recommended to apply marigold epoxy red oxide/ epoxy zinc phosphate grey/ epoxy zinc chrome yellow primer as first coat. Depending upon the service conditions two coats of primer of intermediate coat like marigold hb mio coatings can be applied as second or third coat. For highly corrosive environments two coats of eurothane polyurethane is recommended.



EUROTHANE POLYURETHANE PAINTS ACRYLIC ALIPHATIC POLYURETHANE FINISHING PAINT

Conventional spray application setting:

Thinner : pu thinner 099

Addition : 5-15% nozzle orifice : 1.2-1.4 mm nozzle pressure : 40-50 psi

Airless spray application setting:

Thinner : pu thinner 099
Addition : max 5%, if required.

Nozzle orifice : 0.28 mm Nozzle pressure : 1800-2200 psi

> Note

Pu hardener is very sensitive to moisture. Keep the containers tightly closed, each time after use. Normal thinners can ruin the pu finish. Use only thinner 099.

> Surface Preparation

This is being top coat, to be applied over primed surface, selection of primer(s) and method of surface preparation are of prime importance for the success of whole coating system. Apply eurothane polyurethane finish paint on well primed surface which free from dirt and other contaminants. If aged coatings are already there, sand it with 400/600 sand paper before application of finish paint.

> Health And Safety

Polyurethane paints contains free organic isocynate compound. Mixing and handling of this product this paints must be carried out with taking proper safety measures to avoid skin contacts, eye contacts, and inhalation of solvent vapours and mist of the paint spray. The painting must be carried out in a well ventilated spray booths fitted with proper exhaust systems. If painting is to be done on site, care must be taken that along with the spray painter; other people in the nearby area are also protected in the same manner as the painter. Polyurethane paints if swallowed immediately contact a doctor.

Disclaimer

The information contained within this data sheet is based on information believed to be reliable at the time of its preparation. The company will not be liable for any loss or damage whatsoever occurred including liability for negligence, which may be suffered by the user of the data contained herein. It is the users' responsibility to conduct all necessary tests to confirm the suitability of any product or system for their intended use. No guarantee of results is implied since conditions of use are beyond our control.